

Reflex[®] Elefantenhaut

The authentic, robust special paper

202601

What for	How	Why
Bookbinding Brochures Folders and Binders Annual Reports Stationery Certificates Notebooks Menus and Greeting cards Packaging Bags Origami	Offset printing Thermo-relief printing UV drying Oil-based varnishes UV varnishes Dispersion varnishes Embossing Drilling and perforating Scoring, folding and die cutting Binding Inkjet- and Laserprint	Every sheet is unique Typical and distinctive veining Unmarked by grease and dirt Wipeable Resistant to scratches and abrasion Highly resistant to tearing

What exactly

Prüfkriterien	Einheit				Normen
Flächenmasse	g/m ²	110	125	190	EN ISO 536
Dicke	µm	125	145	230	EN 20534
spez. Volumen	cm ³	1,1	1,15	1,2	DIN 53105
Oberflächen	pH	6,5	6,5	6,5	DIN53124
Glätte	Sek.	25	25	25	DIN 53107
Spez. Steifigkeit I/s	%	0,9 0,3	1,1 0,3	3,0 1,3	DIN 53121 angle 7,5°
Opazität	%	>90	>90		DIN 53416/ISO 2471



The mark of responsible forestry



Certified by the DQS:
 ISO 9001
 ISO 14001
 ISO 50001

Given values are targets and are subject to alterations.
 The information given is our current knowledge.
 We recommend own tests before using material for the first time.